

# (12) United States Patent

### MacAdams et al.

### (54) BONDING OF COMPOSITE MATERIALS

(71) Applicant: Cytec Industries Inc., Woodland Park,

NJ (US)

(72) Inventors: Leonard MacAdams, Woolwich

Township, NJ (US); Dalip Kohli,

Churchville, MD (US)

Assignee: CYTEC INDUSTRIES INC.,

Woodland Park, NJ (US)

(\*) Notice: Subject to any disclaimer, the term of this

patent is extended or adjusted under 35

U.S.C. 154(b) by 462 days.

(21) Appl. No.: 14/339,905

(22)Filed: Jul. 24, 2014

(65)**Prior Publication Data** 

> US 2015/0056433 A1 Feb. 26, 2015

## Related U.S. Application Data

- Provisional application No. 61/868,640, filed on Aug. 22, 2013.
- (51) **Int. Cl.** B29C 65/00 (2006.01)B32B 7/06 (2006.01)(Continued)
- (52) U.S. Cl.

CPC ...... B29C 66/0224 (2013.01); B29C 65/02 (2013.01); B29C 65/4835 (2013.01); B29C 65/5057 (2013.01); B29C 66/1122 (2013.01); B29C 66/30322 (2013.01); B29C 66/45 (2013.01); B29C 66/721 (2013.01); B29C 66/7394 (2013.01); **B29C** 66/73161 (2013.01); B29C 66/73751 (2013.01); B32B 5/02 (2013.01); B32B 5/12 (2013.01); B32B 7/06 (2013.01); B32B 7/12 (2013.01); B32B 27/38 (2013.01); B32B 37/0038 (2013.01); B32B 37/025 (2013.01); B32B 37/12 (2013.01); (Continued)

US 9,636,867 B2 (10) Patent No.: (45) **Date of Patent:** 

May 2, 2017

### (58) Field of Classification Search

CPC ...... B29C 66/0224; B29C 66/712; B29C 66/73753; B32B 37/0038; B32B 37/025; B32B 37/144; B32B 38/10; B32B 2305/74; C08J 5/24

USPC ...... 156/152, 182, 230, 231, 238, 241, 247, 156/249, 307.1-307.7, 714

See application file for complete search history.

### (56)References Cited

### U.S. PATENT DOCUMENTS

11/2003 Reis et al. 6.645.610 B1 9,193,129 B2\* 11/2015 Rogalski ...... B32B 3/18 (Continued)

### FOREIGN PATENT DOCUMENTS

JP 61252284 A \* 11/1986

### OTHER PUBLICATIONS

Machine translation of JP 61252284 date unknown.\*

Primary Examiner - John Goff (74) Attorney, Agent, or Firm — Thi Dang

#### (57)**ABSTRACT**

Peel ply for surface preparation and a method of surface preparation prior to adhesive bonding. A resin-rich peel ply is applied onto a curable, resin-based composite substrate, followed by co-curing. After co-curing, the composite substrate is fully cured but the matrix resin in the peel ply remains partially cured. When the peel ply is removed, a roughened, bondable surface with chemically-active functional groups is revealed. The composite substrate with the chemically-active, bondable surface may be bonded to another composite substrate to form a covalently-bonded structure.

### 13 Claims, 8 Drawing Sheets

